

Filler Pro 696

Product properties

Filler for gypsum board in dry rooms. Contains light fine-grained filler paste with good filling capacity and high strength. Finish by treating with a wall covering and/or suitable ceiling or wall paint in the desired colour and gloss.

- Gypsum board joints
- High tensile strength
- Beige



Labelling



Product use

Filling and reinforcing of joints with Flügger approved CE labelled gypsum tape and filling screw holes on gypsum plasterboard.

Patching and filling when smoothing out plaster, concrete, lightweight concrete, gypsum plasterboard and previously painted surfaces.

Substrate

Must be clean, dry, firm and suitable for surface treatment.

Treatment

Remove loose material and paint by cleaning, sanding and dusting.

Remove dirt, grime, grease and chalking materials by cleaning with Fluren 37.

Water-soluble discolouration, nicotine and soot can be cleaned with Fluren 49.

Sand flat hard, slippery surfaces.

Apply the filler paste and smooth out.

Dust off and fill the gypsum board joints and place the plaster tape with the prefabricated fold against the joint, pressing firmly with the knife and pressing down into the wet filler paste.

Press the tape in so far that a thin layer of filler paste is deposited on the outside of the tape.

At the same time, scrape the filler over the tape.

Once it has dried, fill the joints and screw holes twice.

Sand the surface and prime it before any additional treatment.

Application

Apply and smooth out using a filler knife.

Decide your choice of tools based on the size of the surface.

Apply a sufficient amount and then work and smooth out the filler paste.

Cold/ heat can affect the viscosity of the material.

Condensation during drying/curing must not form.

Cold and increased humidity extends drying time, full curing and recoating interval.

Increased temperature and low atmospheric humidity reduce drying time and full curing.

Risk of shrinkage where the filler paste is not completely cured before additional treatment.

Always perform a test treatment for a check and acceptance of adhesion and result.

Expected result

Even surface for additional treatment.

Please note!

Install the gypsum board according to the manufacturer's instructions and standards.

See the Flügger user directions for gypsum board, filling of joints.

Environmental information

Minimize your paint waste by pre-estimating how much filler you need.

Remove as much filler as possible from tools before cleaning.

Filler and cleaning fluid must not be poured down drains, but collected and disposed of as environmental waste.

Empty and dry packaging should be sorted as plastic, metal handles should be removed and sorted as metal.

Store excess filler correctly so that leftovers can be used and environmental impact is minimised.

Storage

Cool, frost-free, and tightly closed

Protection equipment

Protect skin and eyes from splashes with suitable clothing, gloves and glasses.

Avoid inhalation of spray mist and grinding dust.

Wear suitable protective equipment, see safety data sheet for further information.

Technical Data

Color (plaster)	Beige
Density (kgs/l)	1.29
Solids Weight %	57
Solids Vol. %	51
Nominal spreading rate (m²/ltr.)	1
Min. working temp. during application and drying/curing	Min. +10°C
Humidity	Max. humidity 80 % RH.
Drying time at 20° C, 60 % RH (Hours)	2
Recoatable at 20° C, 60 % RH (Hours)	20
Fully cured at 20° C, 60 % RH (Days)	28
Emission acc. to ISO 16000-9:2011 (< µg/m²h after 28 days)	67
Adhesion on concrete (MPa)	0.72
Layer thickness (nominal mm)	2
Grain size (max. Mm)	0.2
Cleaning of Tools etc.	Water
Country of Origin	Sweden

Current TDS Version

October 2025